

SPECIFICATION

FABRIC:	Style 1200 Vinex[®] 85% Vinal / 15% Polynosic 3 x 1 Twill
WIDTH – (Inches, Minimum, Selvedge included): ASTM D3774	59
YARNS PER INCH – (Minimum, Warp and Fill): ASTM D3775	110 x 58
WEIGHT – (Oz/sq yd, Minimum): ASTM D3776	8.5
BREAKING STRENGTH – (Pounds, Minimum, Warp and Fill): ASTM D5034	180 x 100
TEARING STRENGTH – (Pounds, Minimum, Warp and Fill): ASTM D1424	8.0 x 6.0
SHRINKAGE – (% , Maximum): AATCC 135 (3, V, Aiii) 5 Laundry Cycles Warp and Fill	3.0
FLAMMABILITY: ASTM D 6413	
After Flame, Seconds (Maximum)	2.0
Char Length, Inches (Maximum)	5.0

Vinex[®] is a trademark of Westex Inc.