

**SPECIFICATION**

<b>FABRIC:</b>	<b>Style 801 INDURA® Ultra Soft® 88% Cotton/12% High Tenacity Nylon Napped Sateen</b>
<b>WIDTH</b> – (Inches, Minimum, Selvedge included): ASTM D3774	59
<b>YARNS PER INCH</b> – (Minimum, Warp and Fill): ASTM D3775	88 x 40
<b>WEIGHT</b> – (Oz/sq yd, Minimum): ASTM D3776	13.0
<b>BREAKING STRENGTH</b> – (Pounds, Minimum, Warp and Fill): ASTM D5034	100 x 145
<b>TEARING STRENGTH</b> – (Pounds, Minimum, Warp and Fill): ASTM D1424	6.5 x 10.0
<b>SHRINKAGE</b> – (% , Maximum): Federal Test Standard 191A Method 5550 Warp and Fill	3.0
<b>FLAMMABILITY:</b> ASTM D6413	
After Flame, Seconds (Maximum)	2.0
Char Length, Inches (Maximum)	5.0

This fabric meets the requirements of ASTM F1506, NFPA 70E Level 2,  
and OSHA 29 CFR 1910.269.

**INDURA® and INDURA® Ultra Soft®** are trademarks of Westex Inc.

07/30/02