

SPECIFICATION

FABRIC:	Style 961 INDURA® Ultra Soft® 88% Cotton/12% High Tenacity Nylon Rough House Duck
WIDTH – (Inches, Minimum, Selvedge included): ASTM D3774	59
YARNS PER INCH – (Minimum, Warp and Fill): ASTM D3775	85 x 25
WEIGHT – (Oz/sq yd, Minimum): ASTM D3776	11.0
BREAKING STRENGTH – (Pounds, Minimum, Warp and Fill): ASTM D5034	130 x 120
TEARING STRENGTH – (Pounds, Minimum, Warp and Fill): ASTM D1424	6.0 x 8.0
SHRINKAGE – (% , Maximum): Federal Test Standard 191A Method 5550 Warp and Fill	3.0
FLAMMABILITY: ASTM D6413	
After Flame, Seconds (Maximum)	2.0
Char Length, Inches (Maximum)	5.0

This fabric meets the requirements of ASTM F1506, NFPA 70E Level 2,
CGSB 155.20 and OSHA 29 CFR 1910.269.

INDURA® and INDURA® Ultra Soft® are trademarks of Westex Inc.